

**Our ref.-Nr.** : 22001006D

**Report date** : 9/09/2022

## REPORT OF ANALYSIS

Page 1/2

**Type** : Received sample  
**Sample reference** : Whitewood Premium Wood pellets - EE001  
**Sample material** : Wood pellets ENplus A1  
**Order number** : n/a  
**Date received** : 26/08/2022  
**Received from** : Prima Invest SPRL  
**Preparation** : As per ISO 14780 <sup>(a)</sup>  
**Analyses** : Results were found to be as follows:

Parameter	Method	Unit	Specifications	As received	Dry base
<b>ENplus required parameters</b>					
Total Moisture <sup>(a)</sup>	ISO 18134	%	≤ 10	5,2	***
Ash <sup>(a)</sup>	ISO 18122	%	≤ 0,7	***	0,32
Sulphur <sup>(a)</sup>	ISO 16994	%	≤ 0,04	***	0,01
Net Cal. Value (q <sub>p,net</sub> ) <sup>(a)</sup>	ISO 18125	kWh/kg	≥ 4,6	5,016	***
Nitrogen (N) <sup>(a)</sup>	ISO 16948	%	≤ 0,3	***	0,10
Chlorine (Cl)	ISO 16994	%	≤ 0,02	***	0,0012
Bulk density <sup>(a)</sup>	ISO 17828	kg/m <sup>3</sup>	600 ≤ BD ≤ 750	680	***
Mechanical durability <sup>(a)</sup>	ISO 17831-1	%	≥ 98,0	98,8	***
Diameter	ISO 17829	mm	6±1 or 8±1	6,0	***
Length	ISO 17829	mm	3,15 < L ≤ 40	13,5	***
Fines < 3,15 mm round <sup>(a)</sup>	ISO 18846	%	bulk pellets ≤ 1,0	***	***
			bagged pellets ≤ 0,5	0,2	***
<b>Additional parameters</b>					
Gross Cal. Value (q <sub>v,gr</sub> ) <sup>(a)</sup>	ISO 18125	kJ/kg	***	***	20.448
		kcal/kg	***	***	4.884
		kWh/kg	***	***	5,680
Carbon (C) <sup>(a)</sup>	ISO 16948	%	***	***	51,0
Hydrogen (H) <sup>(a)</sup>	ISO 16948	%	***	***	6,19
Oxygen (O)	By difference	%	***	***	42,38
Stowage factor	Calculated	m <sup>3</sup> /t	***	1,47	***

<sup>(a)</sup> Performed by Inspectorate Ghent under accreditation certificate Belac 393-TEST

Our ref.-Nr. : 22001006D  
Report date : 9/09/2022

## REPORT OF ANALYSIS

Page 2/2

Type : Received sample  
Sample reference : Whitewood Premium Wood pellets - EE001  
Sample material : Wood pellets ENplus A1  
Order number : n/a  
Date received : 26/08/2022  
Received from : Prima Invest SPRL  
Preparation : As per ISO 14780 <sup>(a)</sup>  
Analyses : Results were found to be as follows:

AFT IN OXIDIZING ATMOSPHERE (ISO 21404) <sup>(1)</sup>			
- Shrinkage temperature (SST)			1094
- Deformation temperature (DT)	°C	≥ 1200	1341
- Hemisphere temperature (HT)			1347
- Flow temperature (FT)			1362

For and on behalf of Bureau Veritas  
Commodities Ghent NV  
Sylvie Rasselle  
Solid Fuels Business Manager

**Our ref.-Nr.** : 22001006D

**Report date** : 9/09/2022

## PHOTOS OF THE SAMPLE

**Type** : Received sample  
**Sample reference** : Whitewood Premium Wood pellets - EE001  
**Sample material** : Wood pellets ENplus A1  
**Order number** : n/a  
**Date received** : 26/08/2022  
**Received from** : Prima Invest SPRL

